



Erosion Control Blanket

Standard Netting – Single Net – 100% Straw (SSNS)

The BMP Standard Double Net Straw (SDNS) Erosion Control Blanket is made of two synthetic nets filled with weed-free agricultural wheat straw. Designed for use on mild slope and channel applications, these short-term blankets are designed to reduce soil erosion and channel sedimentation through a combination of physical and biological means. The Blanket provides an effective and cost-efficient solution to soil erosion and sedimentation control. These blankets also offer a protective vegetative cover that aids in reducing water velocity and sedimentation.

Properties	Test Method	Values
Netting		Top and Bottom (Double) Photodegradable Net
Fill		100% Weed Free Agricultural Wheat Straw
Longevity		Short Term - est. 12 Months
Mass Per Unit Area	ASTM D6475	7 - 8 oz/sq/yd 250 g/m ²
Tensile Strength	ASTM D6818	MD - 8.4 lb/in @ % 27.8 XD - 6.7 lb/in @ % 30.2
Thickness	ASTM D6525	0.250 in 0.630 cm
Light Penetration	ASTM D6567	6.9%
Water Absorption	ASTM D1117	522%
Unvegetated Bench-Scale Rain Splash and Runoff	ASTM D7101	50 mm (2 in.) / hr for 30 min. Soil Loss Ratio† = 40.24 C Factor: 0.052 100 mm (4 in.) / hr for 30 min. Soil Loss Ratio† = 13.19 C Factor: 0.091 150 mm (6 in.) / hr for 30 min. Soil Loss Ratio† = 18.04 C Factor: 0.049
Unvegetated Bench-Scale Shear Stress	ASTM D7207	1.61 psf @ ½ in soil loss (77 Pa)
Seed Germination (ASTM Method)	ASTM D7322	1.79

† Soil Loss Ratio = Soil Loss Bare Soil / Soil Loss with RECP = 1 / C-Factor (Note: soil loss is based on regression analysis)

Roll Dimensions

BMP-SDNS08	8' x 112.5' (100sy / 83.6127 m ²) - ~50 lbs	25 Rolls/Pallet
BMP-SDSNS16	16' x 112.5' (200sy / 167.23 m ²) - ~100 lbs	20 Rolls/ Pallet
BMP-SDNS08JR	8' x 562.5' (500sy / 418.06 m ²) - ~250 lbs	4 Rolls/ Pallet
BMP-SDNS08JR	16' x 562.5' (1000sy / 836.13 m ²) - ~500 lbs	4 Rolls/ Pallet

Shipping From:

#50-183073 RR 150,
Brooks, Alberta T0J 2A0
Canada, County of Newell

The information contained herein is furnished without charge or obligation and the recipient assumes all responsibility for its use. Because conditions of use and handling may vary and are beyond our control, we make no representation about, and are not responsible or liable for the accuracy and reliability of said information or the performance of any product. Any specification, property or application listed herein are provided as information only and in no way modify, amend, enlarge or create any warranty. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.